N° 1489
CONSIGLIO NAZIONALE CHIMICI

CENTRO SERVIZI TESSILI s.r.l.
Laboratorio analisi chimiche e prove fisiche

Lab. ref. N°19333

Customer : W&L Jordan GmbH

Date received: 01/02/19
Date issued: 05/02/19
Article : Rope 711405

PHYSICAL TESTS	RESULT	TESTING METHODS
Ignitability of upholstery composites **Ignition source 0 : cigarette**	**Results :** *Post Ignition* : no *flame*: no *smoke* : no **Extent of damage to component :** Horizontal : Width : 26 mm , Length: 39 mm Vertical : Width : 26 mm , Length: 35 mm **Result : PASS**	**EN 1021 - 1** ***Identification and construction of test specimens* : CMHR d=24-26 Kg/m³ in a seat/back configuration and covered by the fabric to be tested.** ***Time of ignition : 20 sec.*** ***Conditioning of material* : 48hr - 20°C - 65% r.h.**
Ignitability of upholstery composites **Ignition source 1 : butane**	**1st flame application:** On contact with the butane flame the cover material does not melt but ignite. The sample ignite after removal of the flame and burn for 1 sec. Smoke duration and smouldering 10 sec. **Extent of damage to component :** Horizontal : Width : 31 mm , Length: 19 mm Vertical : Width : 35 mm , Length: 81 mm **Result : sample Pass the test. Not Ignition**	**EN 1021 - 2** ***Identification and construction of test specimens* : CMHR d=24-26 Kg/m³ in a seat/back configuration and covered by the fabric to be tested.** ***Time of ignition : 20 sec.*** ***Conditioning of material* : 48hr - 20°C - 65% r.h.**

I risultati enunciati si riferiscono esclusivamente al campione testato, e non a lotti o partite di pezze. I campioni verranno da noi conservati 30 gg. dalla data di emissione del rapporto,oltre i quali non saremo più responsabili di eventuali contestazioni.

Tecnico analista
Cristiano Benigni

Direttore di laboratorio
Dott. Simone Calamai

ORDINE DEI CHIMICI DELLA TOSCANA
DOTT. SIMONE CALAMAI N° 1489

Via 5 giornate di Milano n°24 **59100 PRATO**
Tel .+39 0574 622887 fax +39 0574 1660601 **e-mail: centroservizitessili@libero.it**