N° 1489
CONSIGLIO NAZIONALE CHIMICI

# *CENTRO SERVIZI TESSILI s.r.l.*
## *Laboratorio analisi chimiche e prove fisiche*

**Lab. ref. N° 24673**

Customer : **W & L. JORDAN GMBH**
Date received: 22/07/21
Date issued: 29/07/21
Article: BLANKET 711 406

| PHYSICAL TESTS | RESULT | TESTING METHODS |
|---|---|---|
| **Ignitability of upholstery composites**<br><br>**Ignition source 0 : cigarette** | **Results :**<br>*Post Ignition* : no<br>*flame*: no<br>*smoke* : no<br><br>**Extent of damage to component :**<br>Horizontal : Width : 18 mm , Length: 29 mm<br>Vertical : Width : 16 mm , Length: 29 mm<br><br>**Result : PASS** | **EN 1021 - 1**<br><br>***Identification and construction of test specimens* : CMHR d=24-26 Kg/m³ in a seat/back configuration and covered by the fabric to be tested.**<br>***Time of ignition : 252 sec.***<br>***Conditioning of material* : 48hr - 20°C - 65% r.h.** |
| **Ignitability of upholstery composites**<br><br>**Ignition source 1 : butane** | **1st flame application:**<br>On contact with the butane flame the cover material does not melt but ignite.<br>The sample ignite after removal of the flame and burn for 2 sec. Smoke duration and or smouldering 4 s.<br>**Extent of damage to component :**<br>Horizontal : Width : 56 mm , Length: 37 mm<br>Vertical : Width : 65 mm , Length: 87 mm<br><br>**Result : sample Pass the test. Not Ignition** | **EN 1021 - 2**<br><br>***Identification and construction of test specimens* : CMHR d=24-26 Kg/m³ in a seat/back configuration and covered by the fabric to be tested.**<br>***Time of ignition : 20 sec.***<br>***Conditioning of material* : 48hr - 20°C - 65% r.h.** |

I risultati enunciati si riferiscono esclusivamente al campione testato, e non a lotti o partite di pezze. I campioni verranno da noi conservati 30 gg. dalla data di emissione del rapporto,oltre i quali non saremo più responsabili di eventuali contestazioni.

Tecnico di laboratorio
Cristiano Benigni

Responsabile di laboratorio
Dott. Simone Calamai

ORDINE DEI CHIMICI DELLA TOSCANA
DOTT. SIMONE CALAMAI N° 1489

**Via 5 giornate di Milano n°24** **59100 PRATO**
**Tel .+39 0574 622887 fax +39 0574 1660601** **e-mail: centroservizitessili@libero.it**